



Development and optimization of a new formaldehyde-free cornstarch and tannin wood adhesive

A. Moubarik, Bertrand Charrier, Ahmed Allal, Fatima Charrier, A. Pizzi

► To cite this version:

A. Moubarik, Bertrand Charrier, Ahmed Allal, Fatima Charrier, A. Pizzi. Development and optimization of a new formaldehyde-free cornstarch and tannin wood adhesive. European Journal of Wood and Wood Products, 2009, 68 (2), pp.167-177. 10.1007/s00107-009-0357-6 . hal-00568244

HAL Id: hal-00568244

<https://hal.science/hal-00568244>

Submitted on 23 Feb 2011

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



Draft Manuscript for Review

Development and optimization of a new formaldehyde-free cornstarch and tannin wood adhesives

Journal:	<i>Holz als Roh- und Werkstoff</i>
Manuscript ID:	HRW-08-0144.R1
Manuscript Type:	ORIGINALARBEITEN / ORIGINALS
Date Submitted by the Author:	09-Apr-2009
Complete List of Authors:	MOUBARIK, Amine; Université de Pau et des Pays de l'Adour, SYLVADOUR CHARRIER, Bertrand; Université de Pau et des Pays de l'Adour, SYLVADOUR CHARRIER, Fatima; Université de Pau et des Pays de l'Adour, SYLVADOUR Allal, Ahmed; Université de Pau et des Pays de l'Adour, Equipe de physique et Chimie des Polymères Pizzi, Antonio; Université de Nancy 1, ENSTIB
Keywords:	Cornstarch, Formaldehyde, Hexamine, Mimosa tannin, Quebracho tannin, Wood adhesives, Wood composites



Development and optimization of a new formaldehyde-free cornstarch and tannin wood adhesive

A. Moubarik, B. Charrier, A. Allal, F. Charrier, A. Pizzi

Abstract

The development and optimization of a new, environment-friendly adhesive made from abundant and renewable cornstarch and tannin is described in this study. At present, the production of wood composites mainly relies on petrochemical- and formaldehyde-based adhesives such as phenol-formaldehyde (PF) resins and urea-formaldehyde (UF) resins. Formaldehyde-free cornstarch plus tannin adhesives were evaluated for mechanical and physical properties (shear strength, rheological characterisation and thermogravimetric analysis).

First, optimized conditions for the preparation of cornstarch-sodium hydroxide wood adhesives were determined. The parameters studied were the following: total solids content of the adhesives, sodium hydroxide concentration and sodium hydroxide/cornstarch volume ratio. The highest shear strength results appeared to be 0.5 sodium hydroxide / cornstarch volume ratio when using concentrations of cornstarch (65 % p/v H₂O) and sodium hydroxide (33 % p/v H₂O). The optimum cure temperature was 170°C and the cure time 4min. The addition of two types of tannin-based adhesives, Mimosa and Quebracho, with hexamethylenetetramine (hexamine) hardener to the cornstarch-sodium hydroxide formulation improved the shear strength and decreased the viscosity of adhesives.

Entwicklung und Optimierung eines neuen, formaldehydfreien Holzklebstoffes auf Maisstärke- und Tanninbasis

Zusammenfassung

In dieser Studie wird die Entwicklung und Optimierung eines neuen, umweltfreundlichen Klebstoffes auf Basis der nachwachsenden und reichlich vorhandenen Rohstoffe Maisstärke und Tannin beschrieben. Gegenwärtig werden zur Herstellung von Holzwerkstoffen Klebstoffe auf Öl- und Formaldehydbasis, wie zum Beispiel Phenolformaldehyd-Harz (PF) und Harnstoffformaldehyd-Harz (UF), verwendet. Die mechanischen und physikalischen Eigenschaften (Scherfestigkeit, rheologische Eigenschaften und thermogravimetrische Analyse) von Klebstoffen auf Maisstärke und Tanninbasis wurden untersucht.

Zunächst wurden die optimalen Bedingungen zur Herstellung von Maisstärke-Natriumhydroxid-Holzklebstoffen bestimmt. Dabei wurden die Parameter Gesamt-Feststoffgehalt der Klebstoffe, Natriumhydroxidkonzentration und das Volumenverhältnis von Hydroxid und Maisstärke untersucht. Die höchste Scherfestigkeit ergab sich bei einem Volumenverhältnis von 0,5 bei einer Maisstärkekonzentration von 65% p/v H₂O und einer Natriumhydroxidkonzentration von 33% p/v H₂O. Die optimale Aushärtungstemperatur lag bei 170°C und die Aushärtungszeit bei 4 Minuten. Durch Zugabe zweier verschiedener Tannin basierter Klebstoffe, Mimosa und Quebracho, mit Hexamin als Härter, zur Maisstärke-Natriumhydroxid-Rezeptur wurde die Scherfestigkeit verbessert und die Viskosität der Klebstoffe verringert.

A. Moubarik (✉), F. Charrier, B. Charrier

Sylvadour, IUT des Pays de l'Adour, 371 rue du Ruisseau, BP 201, 40004 Mont de Marsan, France.
amine.moubarik@etud.univ-pau.fr

A. Pizzi

ENSTIB-LERMAB, Nancy University, Epinal, France

A. Allal

IPREM-EPCP (UMR 5254), Université de Pau et des Pays de l'Adour, Pau, France

1 Introduction

One of the main concerns of the 21st century is the environment. The environment has become a subject of constant attention and has become a focal point of our life and welfare (Meyer et al. 1986 a, b, c).

Formaldehyde-based wood adhesives such as phenol-formaldehyde, urea-formaldehyde and melamin-urea-formaldehyde are derived from petrochemicals, which are non-renewable and therefore ultimately limited in supply (Li *et al.* 2004). Moreover, formaldehyde is considered a priority pollutant by the United States Environmental Protection Agency. Its emission into the environment and exposure of workers at manufacturing facilities continues to be a major safety concern (Keith and Tellier 1979, Myers 1986).

Efforts are made to develop durable adhesives using phenolic substitutes (Thompson 1991). Other investigators have utilized renewable natural polymers to replace phenol in phenol-formaldehyde adhesives (Conner *et al.* 1989, Conner 1989). Lignin, a highly branched natural phenolic polymer and a by-product of the pulping industry, is an abundant renewable resource at

1 low cost (Pizzi 2006). Tannin is another example of such a renewable material and has been used
2 to substitute tannin for the synthetic phenolics in wood adhesives (Pizzi 2006).

3 Starch is one of the most abundant natural polymers (Imam et al. 1999). Starch has been used as
4 an adhesive in a wide range of products, including binders, sizing material, glues and pastes
5 (Imam et al. 1999, Yazaki and Collins 1997). More recently, the development of a starch-based
6 wood adhesive for interior applications has been described (Imam et al. 1999). Starch yields
7 adhesives with excellent affinity for polar materials such as cellulose. Ideally, the contact angle
8 between the adhesive and the substrate should be small. This allows the adhesive to wet the
9 surface and spread uniformly in a thin film with a minimum of voids. In this regard, starch based
10 adhesives wet the polar surface of cellulose, penetrate crevices and pores and, thus, form strong
11 adhesive bonds (Imam et al. 1999).

12 Among the possible alternatives, tannin is an excellent renewable resource which can be used for
13 replacing petroleum-derived phenolic compounds. The major species from which it can be
14 obtained are Mimosa, Quebracho and Radiata pine. The use of hexamine as a hardener for a
15 tannin, hence, a tannin-hexamine adhesive, is a very environment-friendly proposition. ^{13}C -NMR
16 has confirmed (Pichelin et al. 1999, Kamoun et al. 2003) that the main decomposition of
17 hexamine under such conditions is not directly due to formaldehyde. It rather proceeds through
18 reactive intermediates, hence, mainly through the formation of reactive imines and
19 iminoaminomethylene bases. ^{13}C -NMR has also confirmed (Pichelin et al. 1999, Kamoun et al.
20 2003) that in the presence of chemical species with very reactive nucleophilic sites, such as
21 condensed flavonoid tannins, hexamine is not a formaldehyde-yielding compound. It neither
22 decomposes to formaldehyde and ammonia in an acid environment nor to formaldehyde and
23 trimethylamine in an alkaline environment (Pizzi and Tekely 1995, 1996; Pizzi et al. 1996,
24 Kamoun et al. 2003). The very reactive imines and iminoaminomethylene intermediates initially
25 formed in its decomposition do react with the phenolic species present without ever passing
26 through the formation of formaldehyde (Pizzi and Tekely 1995, 1996; Pizzi et al. 1996; Kamoun
27 et al. 2003).

28 Initial investigations on the use of wattle tannin in starch corrugating adhesives were carried out
29 at the Division of Forest Products, CSIRO, in 1968. As an alternative material to resorcinol was
30 urgently needed in 1969, the project was extended to include some studies designed to establish
31 reasons for the poor performance of water-resistant starch adhesives (McKenzie and Yuritta
32 1972). Further research and developments in the field of fortified starch adhesives with wattle
33 tannin were carried out in South Africa (Saayman and Brown 1977). Industrial production with
34 one such system started, however, in South Africa in the late 1970's (Custers et al. 1979).

In this study, the mechanical properties (shear strength) and physical properties (rheological and thermogravimetric analysis) of cornstarch-tannin adhesives with hexamine as hardener was investigated.

2 Experimental methods

2.1 Preparation of cornstarch-tannin adhesives and preparation of two-ply wood composites bonded with the cornstarch-tannin adhesives.

Cornstarch water solutions were prepared at six different concentrations namely 12, 25, 50, 65, 75 and 90%, by dissolving cornstarch in deionised water, stirring at room temperature, and adding sodium hydroxide ($M_w = 40.00$) at different concentrations (5, 15, 33, 50 and 75%) as hardeners. The resulting adhesives were mixed for 45 min at room temperature and then used for bonding wood veneer.

In order to improve the shear strength of cornstarch-sodium hydroxide adhesives, the two types of tannin, Mimosa and Quebracho, were added in proportions of 5%, 10%, 20%, 30%, 40% and 50% by weight on cornstarch solids content; hardener content used was 5 percent hexamine by weight on tannin extract solids content. The hexamine was dissolved in water to yield a 30 percent concentration solution in water prior to adding to the tannin solution to form the glue-mix.

Maritime pine veneer with a thickness of 3 mm was cut to rectangular specimens $2.5 \times 11.5 \text{ cm}^2$ (according to British Standard 1204, 1965, part 2, for synthetic resins adhesives). The adhesive was applied to one side of each piece of veneer. The application area was $2.5 \times 2.5 \text{ cm}^2$ for each veneer. The spread rate of the adhesive was 120-150 g/m² on a dry weight basis (Nihat and Nilgül 2002, Pizzi 1977). Two adhesive-coated veneer boards were lapped together with the grain parallel to each other and then pressed at 0.45 MPa (Fig. 1). The press temperature and press time were varied for the determination of their effects on the strength of wood composites. After bonding, the assemblies were conditioned in a Vötsch climate room (25°C and 65% humidity) for 24 hrs. Five hundred samples were prepared for mechanical tests.

2.2 Mechanical properties

The shear strength of the wood composite was determined on an Instron testometric M500-50 AT testing machine. The crosshead speed was 1 mm/min. The load at fraction was measured, and reported as shear strength.

Every experiment was repeated; at least, ten replicates and their standard deviations were calculated.

2.3 Rheological characterization

The adhesives were tested with an advanced rheometric expansion system (ARES) with parallel plate's geometry, which was used for all the measurements; the plate diameter used was 25mm and the gap between the parallel plates was 1.5mm. Silicone oil was used to prevent water evaporation.

2.4 Thermogravimetric analysis (TGA)

Thermogravimetric analysis (TGA) was carried out with a TGA Q50 thermogravimetric apparatus. Ten milligrams of each cured sample was placed on a balance located in the furnace and heat was applied over a temperature range from room temperature to 600 °C at a heating rate of 5 °C/min in air.

2.5 Solid phase ^{13}C NMR analysis

The solid state ^{13}C NMR spectra of the cornstarch, cornstarch-NaOH, mimosa tannin-hexamine and cornstarch-NaOH-MT-H resin systems used, were acquired at ambient temperature by using a Bruker 400 MHz spectrometer. Powdered samples were packed in 4-mm zirconia rotors, sealed with Kel-FTM caps and spun at 6 KHz and at a contact time of 3.5 ms. Chemical shifts were determined relative to tetramethyl silane (TMS) used as control.

3 Results and discussion

First, the conditions for the preparation of cornstarch-sodium hydroxide wood adhesives were optimized. Parameters like total solids content of adhesives, sodium hydroxide concentration,

1 sodium hydroxide/cornstarch volume ratio, reaction time and reaction temperature were studied.
2 These parameters were varied and their effect on shear strength was studied.
3
4
5

6 **3.1 Effects of the total solids content of adhesives on shear strength**

7

8
9
10 The results presented in Table 1 show the effect of cornstarch concentration on shear strength.
11 Table 1 shows that there is an optimum level of cornstarch to be added during formulation to
12 obtain optimal shear strength. As the cornstarch concentration increases, the shear strength and
13 percentage of wood failure increase too. The shear strength increases up to approximately 65%
14 and remains unchanged with a further increase in cornstarch concentration. A total solid content
15 of 65% appears to be optimal. Furthermore, the test revealed that in most cases, joint failure was
16 cohesive in the wood (wood failure) and not due to failure either at the interface or of the
17 adhesive itself. It is interesting to note that, when the total solids content was higher than 65%,
18 the cornstarch-sodium hydroxide adhesive became so viscous that it was difficult to apply.
19
20
21
22
23
24
25
26
27
28
29
30
31
32

33 **3.2 Effects of sodium hydroxide concentration on shear strength**

34

35
36 The results of the effect of sodium hydroxide concentration on the shear strength are shown in
37 Table 2. It can be seen from Table 2 that shear strength values and percentage wood failure
38 increase up to a sodium hydroxide concentration of 33%. Beyond this a decrease in shear strength
39 and percentage of veneer failure is observed. It has been shown that the presence of sodium
40 hydroxide accelerates the reaction between the two polymers amylose and amylopectin due to an
41 increase in pH of the basic medium (Yazaki and Collins 1997; Kennedy 1989; Leach *et al.* 1961;
42 Champagne *et al.* 1985). It is concluded that 33% sodium hydroxide concentration is optimal for
43 the preparation of cornstarch-sodium hydroxide adhesives.
44
45
46
47
48
49
50
51

52 **3.3 Effects of sodium hydroxide/cornstarch volume ratio on shear strength**

53

54
55 Table 3 reports the results of the effect of sodium hydroxide/cornstarch volume ratio on shear
56 strengths of wood composites. It is observed that shear strength and percentage of veneer failure
57 increase up to sodium hydroxide/cornstarch volume ratio of 0.5. Beyond this a decrease in shear
58 strength is observed.
59
60

strength is observed. At higher sodium hydroxide/cornstarch volume ratios, it appears that crosslink formation is hindered, which reduces the rate of crosslink formation and decreases shear strength (Saayman and Brown 1977, Custers *et al.* 1979).

Comparative solid state CP-MAS ^{13}C NMR spectra of cornstarch and NaOH/cornstarch were also done. The comparative ^{13}C NMR spectra in Figure 2 show that some low molecular weight compounds were produced. This is evident from the appearance of new peaks in the 18-40 ppm and 127-135 ppm region. The production of these low molecular weight compounds is due to the dissociation of intermolecular hydrogen bonding in the amylopectin (Tako and Hizukuri 2002; Yamamoto *et al.* 2006).

The alkaline solution reduces the rigidity as well as the stability of the molecular organization of starch. Therefore, the mobility of the amylose chains is increased, which contributes to the loss of granule architecture (Cardoso 2007).

3.4 Effects of hot-press temperature on shear strength

In Table 4, the results of the effect of reaction temperature on the preparation of adhesives are shown. The adhesives were prepared at 60°C, 80°C, 120°C, 140°C, 160°C, 170°C, 180°C and 200°C. Shear strength and percentage of veneer failure increase with increasing temperature from 80°C to 170°C, and then decrease (Table 4). It appears that crosslink formation starts at 80°C. However, at this temperature, the rate and the extent of crosslink formation are low. With the increase in temperature, rate and extent of network formation increase (Mozaffar *et al.* 2004). This causes the increase in shear strength. With increasing the reaction temperature to 200°C, a decrease in shear strength and percentage of veneer failure is observed. This appears to infer that 170°C is the optimal polymerization temperature.

Using TGA, the thermal decomposition and thermal stability of the adhesive are assessed. Figure 3 shows the TGA curve and its derivative (DTG) of the adhesive at different temperatures. The TGA curve shows that there is an evident mass loss at 175 °C. From this temperature onward the curve decreases initially, indicating cornstarch decomposition. This means that the optimum cure

1 temperature was 170 °C. The results obtained by thermogravimetric analysis confirm the results
2 obtained by the shear strength tests.
3
4
5

6 3.5 Effects of hot-press time on shear strength 7 8

9
10 The shear strength significantly increased when the hot-press time was increased from 2 to 4 min
11 (Table.5). A longer hot-press time means more energy is needed for cross-linking. This is the
12 reason for the improvement of the mechanical properties with increasing press time. Further
13 increase in hot-press time from 4 to 25 min had little effect on the shear strength. With increasing
14 the reaction time to 25 min, a decrease in shear strength was observed. The resin still set but the
15 prolonged reaction time appeared to cause the breakdown of some fraction of the hardened
16 network resulting in a decrease in the shear strength observed (Mozaffar *et al.* 2004). From the
17 above, it appears that, a reaction time of 4 min is optimal for the preparation of cornstarch-NaOH
18 resin.
19
20
21
22
23
24
25
26
27

28 The results in Figure 4 appear to confirm this. Figure 4 shows the variation of the viscoelastic
29 parameters (G' and G'') with time at 170 °C, 1 % strain and 1 rad/s. Here, it can be observed that
30 the elastic modulus (G') and viscous modulus (G'') increase progressively with increasing the
31 time up to 4 min. Beyond this a sharp decrease in G' and G'' is observed. This indicates that the
32 optimum cure time is 4 min. Thus, this rheological characterization confirms the results obtained
33 by the shear strength tests.
34
35
36
37
38
39

40 3.6 Improvement of the shear strength with two types of tannin, hardened with hexamine. 41 42

43 The shear strength of the cornstarch-NaOH wood adhesives was then improved by addition of
44 two types of tannin-based adhesives, mimosa and quebracho, using hexamine as hardener.
45
46
47

48 The results of the effect of addition of tannin (Mimosa or Quebracho) and hexamine on shear
49 strength are shown in Table 6. This clearly illustrates that, in both cases, shear strength increases
50 with an increase of the tannin percentage up to 10%. Beyond this level a decrease in shear
51 strength is observed. A decrease in shear strength is attributed to the high amount of hardener
52 (hexamine); which makes the adhesive very viscous. The addition of mimosa tannin and
53 hexamine (Cornstarch-NaOH-MT-H) improves the mechanical properties of 16% compared to
54 the cornstarch-NaOH adhesives alone.
55
56
57
58
59
60

Pizzi (2006) reported that in the case of Mimosa tannin hardened with hexamine, di- and tri-benzylamine bridges were formed, this being stable bridges. Figure 5 shows this mechanism.

In Figure 6, the comparative solid state CP-MAS ^{13}C NMR spectra of cornstarch, NaOH/cornstarch, mimosa tannin/hexamine and cornstarch-NaOH-MT-H adhesive are shown. The spectra in Figure 6 show that no differences were noticeable between the three solid states CP-MAS ^{13}C NMR spectra of the NaOH/cornstarch, mimosa tannin/hexamine and cornstarch-NaOH-MT-H adhesive. This indicates that the two materials function as a polymer blend rather than co-reacting. One definite interaction is that the use of NaOH necessary for cornstarch also favours the condensation reaction of mimosa tannin with hexamine (Pizzi 1994).

3.7 Viscosity of the natural wood adhesives

The results in Table 7 compare the viscosity of the three natural wood adhesives prepared under their optimal conditions (Cornstarch-NaOH, Cornstarch-NaOH-MT-H and Cornstarch-NaOH-QT-H). Viscosity is measured by the advanced rheometric expansion system (ARES) at 25°C. Table 7 indicates that the addition of tannin (Mimosa or Quebracho) and hexamine to the first formulation (cornstarch-NaOH) decreases the viscosity of the natural adhesives. The addition of tannin mimosa and hexamine (Cornstarch-NaOH-MT-H) decrease the viscosity of 25% compared to the cornstarch-NaOH adhesives (Pizzi 1994; Li and Maplesden 1998).

It is clear that cornstarch-NaOH-MT-H wood adhesive, is the best formulation because it improves the shear strength of 16% and decreases the viscosity of 25% compared to the cornstarch-NaOH adhesives.

3.8 Comparison of the mechanical properties of cornstarch-tannin adhesives with commercial adhesives

The cornstarch-NaOH-MT-H adhesive prepared at optimized conditions was compared with three different types of industrial wood adhesives (urea-formaldehyde, polyvynylacetate adhesive and a polyurethane adhesive) for their mechanical properties (Table 8). The results show that the cornstarch-NaOH-MT-H natural adhesive has comparable mechanical properties to the ones of commercial adhesives under the testing conditions used.

3.9 Effects of moisture and liquid water on shear strength

Table 9 shows the effects of moisture (65, 80 and 90% relative humidity) on the mechanical properties of cornstarch-NaOH-TM-H, urea formaldehyde, vinyl and polyurethane adhesive. After bonding, the assemblies were conditioned in a Vötsch climate room (25°C; 65, 80 and 90% relative humidity) for 7 days. Ten samples were prepared for each resin. It can be seen from Table 9 that Cornstarch-NaOH-TM-H, urea formaldehyde vinyl adhesive and polyurethane adhesive had similar shear strength values at 25°C and 65% relative humidity. Furthermore, the experimental results showed that there was no shear strength deterioration observed between 65% and 90% relative humidity. The results indicate that under moisture conditions, formaldehyde-free cornstarch-NaOH-TM-H adhesive is capable of giving shear strength results which are comparable to those obtained with synthetic resins.

Data for shear strength after 2 hours immersion in liquid water (pH= 7 and 25°C) are summarised in Table 10. After immersion, two-ply wood bonded with cornstarch-NaOH-TM-H resin exhibited poorer values of shear strength compared to samples bonded with the commercial resins (urea formaldehyde, Vinyl and Polyurethane adhesive). These natural adhesives are developed exclusively for interior grade panels, hence for an application different from the traditional tannin adhesives. For this reason their resistance to liquid water has no particular importance.

3.10 Effects of storage time of cornstarch-NaOH-MT-H adhesives on shear strength

The cornstarch-NaOH-MT-H adhesive was prepared, and then stored at room temperature for various times before being applied to the wood veneers to determine the effect of storage time on the shear strength of the joint. With increasing storage time, the shear strength decreased (Figure 7). When the cornstarch-NaOH-MT-H adhesives were stored at room temperature for one day, the shear strength was significantly lower than at a storage time of 45 min. The data fitted well the following equation, using the software: 'Table Curve' (2D Windows V2.03).

$$\sigma = 1.56 + 3.67 \exp\left(-\frac{t}{9.39}\right) \quad (1)$$

1 where σ is the shear strength (MPa) and t the time (days). The adjusted R^2 value was 0.99,
2 indicating a good fit. The decline of shear strength with storage time is still not fully understood.
3
4
5

6 4 Conclusion 7 8

9
10 Cornstarch was used with tannin to form a natural wood adhesive. The cornstarch-tannin
11 adhesive is easy to prepare. The adhesive was developed and optimized for wood bonding. In
12 some countries, cornstarch and tannin are inexpensive renewable polymers. The cost of this
13 adhesive appears to be lower than that of the synthetic phenolic resins traditionally used for wood
14 adhesives. Its main advantage is that it contains no formaldehyde or phenol, both of which are
15 considered as environmental pollutants.
16
17
18
19
20

21 Research is in progress to further improve cornstarch-tannin adhesive formulations by employing
22 other nonvolatile, non-toxic aldehyde hardeners (glyoxal or dioxal).
23
24
25
26
27
28
29
30
31

32 Acknowledgements 33 34

35 The authors would like to thank the "Conseil Général des Landes" (Aquitaine, France) for
36 providing financial support.
37
38
39
40
41

42 References 43 44

45 AFNOR (1996) Norme NF EN 113 : Produits de préservation du bois. Méthode d'essai pour
46 déterminer l'efficacité protectrice vis-à-vis les champignons basidiomycètes lignivores.
47 Détermination du seuil d'efficacité.
48
49

50 BS 1204 : Part 2 (1965) Synthetic resin adhesives (phenolic and aminoplastic) for wood.
51 Specification for close-contact adhesives British Standards Institution
52
53

54 Cardoso MB(2007) from rice starch to amylose crystals: alkaline extraction of rice starch,
55 solution properties of amylose and crystal structure of v-amylose inclusion complexes. Université
56 Joseph Fourier, Grenoble I, France.
57
58
59
60

1
2 Cetin NS, Ozmen N (2002) Use of organosolv lignin in phenol-formaldehyde resins for
3 particleboard production. II. Particleboard production and properties. International Journal of
4 Adhesion & Adhesives 22, 481–486.
5
6

7
8 Champagne ET, Rao RM, Liuzzo JA, Robinson W, Gale RJ, Miller F (1985) Solubility behaviors
9 of the minerals, proteins, and phytic acid in rice bran with time, temperature, and pH. Cereal
10 Chem. 62, 218–222.
11
12

13 Conner AH (1989) Carbohydrates in adhesives: introduction and historical perspective. ACS
14 Symposium series 385, p. 271-288.
15
16

17 Conner AH, Lorenz LF, River BH (1989) Carbohydrate-modified-phenol-formaldehyde resins
18 formulated at neutral conditions. ACS Symposium Series 385. p. 355-369.
19
20

21 Custers PAJL, Rushbrook R, Pizzi A, Knauff CJ (1979) Industrial applications of wattle-
22 tannin/urea-formaldehyde fortified starch adhesives for damp-proof corrugated cardboard,
23 Holzforsch. Holzverwert., 31(6), 131-133.
24
25

26 Imam SH, Mao L, Chen L, Greene RV (1999) Wood adhesive from crosslinked poly(vinyl
27 alcohol) and partially gelatinized starch: preparation and properties. Starch/Stärke 51 (1999) Nr.
28 6, S.225-229.
29
30

31 Kamoun C, Pizzi A, Zanetti M (2003) Upgrading melamine-urea-formaldehyde polycondensation
32 resins with buffering additives. I. The effect of hexamine sulfate and its limits. J. Appl. Polym.
33 Sci. 90, 203–214.
34
35

36 Keith IH, Telliard WI (1979) Priority pollutants. Environ Sci Technol; 13:416-23.
37
38

39 Kennedy HM (1989) Starch- and dextrin-based adhesives. In: Hemingway, R.W., Conner, A.H.
40 (Eds.), Adhesives from Renewable Resources. American Chemical Society, Washington, DC, pp.
41 326–335.
42
43

1 Leach VHW, Schoch TJ, Chessman EF (1961) Adsorption von alkaline das stärkekorn. Starke 13
2 (6), 200–203.

3
4
5
6 Li J, Maplesden F (1998) Commercial production of tannins from radiata pine bark for wood
7 adhesives. IPENZ Transactions, Vol. 25, No. 1/EMCh, 1998.
8
9

10
11 Li K, Geng X, Simonsen J, Karchesy J (2004) Novel wood adhesives from condensed tannins
12 and polyethylenimine. International Journal of Adhesion & adhesives 24, 327-333.
13
14

15
16
17 McKenzie AW, Yuritta JP (1972) Starch tannin corrugating adhesives. Appita 26 (1), 30-34.
18 Meyer B, Andrews BAK, Reinhardt RM (1986a) European formaldehyde regulations: a french
19 view. In: Coutrot D(ed) Formaldehyde release from wood products. American Chemical Society
20 Symposium Series No. 385, Washington, D.C., pp 209-216.
21
22

23
24
25 Meyer B, Andrews BAK, Reinhardt RM (1986b) Formaldehyde release from wood panel
26 products bonded with phenol from aldehyde adhesives. In: Emery JA (ed) Formaldehyde release
27 from wood products. American Chemical Society Symposium Series No. 385, Washington, D.C.,
28 pp 26-39.
29
30

31
32
33
34 Meyer B, Andrews BAK, Reinhardt RM (1986c) Formaldehyde release rate coefficients from
35 selected consumer products. In: Pickrell JA, Griffis LC, Mokler BV, Hobbs CH, Kanapilly GM,
36 Bathija A (eds) Formaldehyde release from wood products. American Chemical Society
37 Symposium Series No. 385, Washington, D.C., pp 40-51.
38
39

40
41
42 Mozaffar AK, Sayed Marghoob A, Ved Prakash M (2004) Development and characterization of a
43 wood adhesive using bagasse lignin. International Journal of Adhesion & Adhesives 24 (2004)
44 485–493.
45
46

47
48
49
50 Myers GE (1986) Resin hydrolysis and mechanism of formaldehyde release from bonded wood
51 products. In: Wood adhesives in 1985: status and needs. Madison, WI, Forest products Research
52 Society. P.77-80.
53
54

55 Nihat SC, Nilgül Ö (2002). Use of organosolv lignin in phenol-formaldehyde resins for
56 particleboard production. I. Organosolv lignin modified resins. International Journal of Adhesion
57 & Adhesives. 22 (6), 477-480.
58
59
60

1 Pichelin F, Kamoun C, Pizzi A (1999) Hexamine hardener behaviour: effects on wood glueing,
2 tannin and other wood adhesives. Holz Roh- Werkst 57 (5), 305–317.

6 Pizzi A (1977) Hot-setting tannin-urea-formaldehyde exterior wood adhesives. Adhes. Age 20:
7 27–35
8
9

11 Pizzi A (1994) Advanced wood adhesives technology. M. Dekker, New York.
12
13
14

15 Pizzi A (2006) Recent developments in eco-efficient bio-based adhesives for wood bonding:
16 opportunities and issues. J. Adhesion Sci. Technol., Vol 20, No.8, pp.829-846.
17
18
19

20 Pizzi A, Tekely P (1995) Mechanism of polyphenolic tannin resin hardening by
21 hexamethylenetetramine: CP-MAS ^{13}C NMR. J. Appl. Polym. Sci. 56:1645-1650.
22
23
24

25 Pizzi A, Tekely P (1996) Hardening mechanisms by hexamethylenetetramine of fast-reacting
26 phenolic wood adhesives - a CPMAS ^{13}C NMR study. Holzforschung 50:277-281.
27
28
29
30

31 Pizzi A, Roll W, Dombo B (1996) Hitzehärtende Bindemittel. USA patent 5,532,330
32
33
34

35 Saayman HM, Brown CH (1977) Wattle-base tannin-starch adhesives for corrugated containers.
36 Forest Prod J 27 (4), 21-25.
37
38
39

40 Tako M, Hizukuri S (2002) Gelatinization mechanism of potato starch. Carbohydr. Res. 48, 397-
41 401.
42
43
44

45 Thompson GE (1991) Demethylated kraft lignin as a substitute for phenol in wood
46 adhesives. M.S.Thesis. Colorado State University.
47
48
49

50 Yamamoto H, Makita E, Oki Y, Otani M (2006) Flow characteristics and gelatinization kinetics
51 of rice starch under strong alkali conditions. Food Hydrocoll. 20, 9-20
52
53

56 Yazaki Y, Collins PJ (1997) Uses of Wattle Extract: Tannin Based Adhesives. Rural Industries
57 Research and Development Corporation. RIRDC Publication N°. 97/72. Chapter 15., pp 127-143.
58
59
60

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

For Peer Review

Table 1

Number of prepared adhesives	Total solids content (%)	Sodium hydroxide concentration (%)	Sodium hydroxide/corn starch volume ratio	Reaction temperature (°C)	Reaction time (min)	Shear strength, (SD), MPa	Veneer Failure (%)
1	12	33	0.5	180	5	1.96 (0.62)	0
2	25	33	0.5	180	5	2.32 (0.11)	0
3	50	33	0.5	180	5	3.28 (0.22)	33
4	65	33	0.5	180	5	3.76 (0.11)	66
5	75	33	0.5	180	5	3.84 (0.22)	66
6	90	33	0.5	180	5	3.88 (0.39)	66

Table 2

Number of prepared adhesives	Total solids content (%)	Sodium hydroxide concentration (%)	Sodium hydroxide/corn starch volume ratio	Reaction temperature (°C)	Reaction time (min)	Shear strength, (SD), MPa	Veneer Failure (%)
1	65	5	0.5	180	5	3.07 (0.35)	33
2	65	15	0.5	180	5	3.32 (0.16)	33
3	65	33	0.5	180	5	3.76 (0.11)	66
4	65	50	0.5	180	5	3.42 (0.07)	33
5	65	75	0.5	180	5	3.37 (0.35)	33

Table 3

Number of prepared adhesives	Total solids content (%)	Sodium hydroxide concentration (%)	Sodium hydroxide/corn starch volume ratio	Reaction temperature (°C)	Reaction time (min)	Shear strength, (SD), MPa	Veneer Failure (%)
1	65	33	0.2	180	5	3.25 (0.30)	33
2	65	33	0.5	180	5	3.76 (0.11)	66
3	65	33	0.8	180	5	2.93 (0.16)	33
4	65	33	1.2	180	5	3.56 (0.05)	33
5	65	33	1.5	180	5	3.44 (0.11)	0
6	65	33	2	180	5	2.88 (0.18)	0

Table 4

Number of prepared adhesives	Total solids content (%)	Sodium hydroxide concentration (%)	Sodium hydroxide/corn starch volume ratio	Reaction temperature (°C)	Reaction time (min)	Shear strength, (SD), MPa	Veneer Failure (%)
1	65	33	0.5	60	5	2.78 (0.08)	0
2	65	33	0.5	80	5	2.84 (0.16)	0
3	65	33	0.5	120	5	3.73 (0.01)	33
4	65	33	0.5	140	5	4.20 (0.16)	33
5	65	33	0.5	160	5	4.39 (0.05)	50
6	65	33	0.5	170	5	4.54 (0.02)	66
7	65	33	0.5	180	5	3.76 (0.11)	66
8	65	33	0.5	200	5	3.5 (0.54)	50

Table 5

Number of prepared adhesives	Total solids content (%)	Sodium hydroxide concentration (%)	Sodium hydroxide/corn starch volume ratio	Reaction temperature (°C)	Reaction time (min)	Shear strength, (SD), MPa	Veneer Failure (%)
1	65	33	0.5	170	1	3.03 (0.12)	25
2	65	33	0.5	170	2	3.22 (0.11)	33
3	65	33	0.5	170	4	4.49 (0.30)	66
4	65	33	0.5	170	5	4.54 (0.02)	66
5	65	33	0.5	170	7	3.81 (0.21)	66
6	65	33	0.5	170	10	4.21 (0.15)	66
7	65	33	0.5	170	15	3.94 (0.28)	66
8	65	33	0.5	170	17	4.31 (0.12)	50
9	65	33	0.5	170	20	4.19 (0.13)	33
10	65	33	0.5	170	25	4.12 (0.10)	33

Table 6

Hardener	Tannin	Percentage of tannin (%)	Shear strength, (SD), MPa	Veneer failure (%)
5 percent hexamine by weight on tannin extract solids content	Mimosa	0	4.49 (0.30)	66
		5	4.65 (0.11)	70
		10	5.21 (0.05)	85
		20	4.62 (0.04)	85
		30	4.19 (0.26)	70
		40	3.99 (0.09)	50
	Quebracho	50	3.53 (0.20)	35
		0	4.49 (0.30)	66
		5	4.65 (0.18)	66
		10	5.00 (0.12)	75

Table 7

Wood adhesives	Viscosity, Pa s Mean ± SD
Cornstarch-NaOH	61239 ± 5045
Cornstarch-NaOH-MT-H	45900 ± 5840
Cornstarch-NaOH-QT-H	47100 ± 3010

Table 8

Wood adhesives	Shear strength, MPa Mean ± SD
Cornstarch-NaOH-MT-H	5.21 ± 0.05
Urea-formaldehyde	5.87 ± 0.15
Vinyl adhesive	5.96 ± 0.47
Polyurethane adhesive	6.03 ± 0.18

Table 9

Vötsch climate room conditions	Shear strength, MPa; Mean \pm SD			
	Cornstarch-NaOH- MT-H	Urea formaldehyde	Vinyl adhesive	Polyurethane adhesive
25°C and 65% R.H	5.21 \pm 0.05	5.87 \pm 0.15	5.96 \pm 0.47	6.03 \pm 0.18
25°C and 80% R.H	5.35 \pm 0.11	5.52 \pm 0.12	5.91 \pm 0.19	6.11 \pm 0.21
25°C and 90% R.H	5.17 \pm 0.04	5.51 \pm 0.09	5.71 \pm 0.08	5.87 \pm 0.06

Table 10

	Shear strength, MPa; Mean \pm SD			
	Cornstarch-NaOH-MT-H	Urea formaldehyde	Vinyl adhesive	Polyurethane adhesive
Before immersion	5.21 \pm 0.05	5.87 \pm 0.15	5.96 \pm 0.47	6.03 \pm 0.18
After immersion	1.07 \pm 0.24	4.21 \pm 0.21	4.93 \pm 0.33	5.39 \pm 0.05
Retention (%)	21	71	83	89




Fig. 1




Fig. 2




Fig. 3




Fig. 4




Fig. 5

For Peer Review




Fig. 6




Fig. 7

Table 1. Effects of total solids content of cornstarch-sodium hydroxide adhesives on shear strength (sodium hydroxide (33%)/cornstarch volume ratio was fixed at the level 0.5; 0.45 MPa; 180°C and 5 min). Ten replicates for each total solid content. SD: Standard deviation.

Table 2. Effect of sodium hydroxide concentration on shear strength (sodium hydroxide/cornstarch (65%) volume ratio was fixed at the level 0.5; 0.45 MPa; 180°C and 5 min). Ten replicates for each NaOH concentration. SD: Standard deviation.

Table 3. Effects of sodium hydroxide/cornstarch volume ratio on shear strength (cornstarch (65%), sodium hydroxide (33%), 0.45 MPa; 180°C and 5 min). Ten replicates for each sodium hydroxide/cornstarch volume ratio. SD: Standard deviation.

Table 4. Effects of hot-press temperature on shear strength (sodium hydroxide (33%)/cornstarch (65%) = 0.5; 0.45 MPa and 5 min). Ten replicates for each hot-press temperature. SD: Standard deviation.

Table 5. Effects of hot-press time on shear strength (sodium hydroxide (33%)/cornstarch (65%) = 0.5; 0.45 MPa and 170°C). Ten replicates for each hot-press time. SD: Standard deviation.

Table 6. Effects of tannin (Mimosa and Quebracho) and hexamine on shear strength at 170°C and 4 min. SD: Standard deviation.

Table 7. Results of viscosity of the three natural wood adhesives prepared under their optimal conditions at 25°C.

Table 8. Mechanical properties of cornstarch-NaOH-MT-H adhesive and commercial adhesives.

Table 9. Shear strength values after 7 days in a Vötsch climate room (25°C; 65%, 80% and 90% relative humidity). Ten replicates for each resin. SD: Standard deviation.

Table 10. Shear strength values before and after 2 h of immersion in water. Ten replicates for each resin. SD: Standard deviation.

Figure 1. Schematic representation of wood sample preparation using cornstarch-tannin crosslinked adhesives. Step A: pressure at 180°C and 0.45 MPa, step B: shear strength test after 24 hrs in a Vötsch climate room (25°C and 65% humidity).

Figure 2. Comparative solid state CP-MAS ^{13}C NMR spectra of cornstarch and NaOH/cornstarch.

Figure 3. TGA and DTG curves of cornstarch-NaOH adhesives, $\beta = 5^\circ\text{C}/\text{min}$.

Figure 4. Time evolution of storage modulus (G') and loss modulus (G'') of cornstarch-NaOH adhesive at 25°C; 1rad/s and 1%.

Figure 5. Schematic diagram of the reaction between tannin and hexamine.

Figure 6. Comparative solid state CP-MAS ^{13}C NMR spectra of cornstarch, NaOH/cornstarch, mimosa tannin/hexamine and cornstarch/NaOH/MT/H.

Figure 7. Effects of storage time of the cornstarch-NaOH-MT-H adhesive on shear strength.

Tabelle 1
Einfluss des Gesamt-Feststoffgehalts des Maisstärke-Natriumhydroxid-Klebstoffs auf die Scherfestigkeit (Natriumhydroxid (33%)/ Maisstärke Volumenverhältnis 0,5; 0,45 MPa; 180°C und 5 Minuten). Zehn Proben je Gesamtfeststoffgehalt. SD: Standardabweichung

Tabelle 2
Einfluss der Natriumhydroxidkonzentration auf die Scherfestigkeit (Verhältnis von Natriumhydroxid/Maisstärke (65%) = 0,5; 0,45 MPa; 180°C und 5 Minuten). Zehn Proben je Natriumhydroxidkonzentration. SD Standardabweichung

Tabelle 3
Einfluss des Volumenverhältnisses von Natriumhydroxid und Maisstärke auf die Scherfestigkeit (Maisstärke 65%, Natriumhydroxid 33%; 0,45 MPa; 180°C und 5 Minuten). Zehn Proben je Natriumhydroxid/Maisstärke Volumenverhältnis. SD Standardabweichung.

Tabelle 4
Einfluss der Temperatur beim Heißpressen auf die Scherfestigkeit (Natriumhydroxid 33%/Maisstärke 65% Volumenverhältnis 0,5; 0,45 MPa und 5 Minuten. Zehn Proben je Presstemperatur, SD Standardabweichung

Tabelle 5

1
2
3 Einfluss der Pressdauer auf die Scherfestigkeit (Natriumhydroxid 33% / Maisstärke 65%
4 Volumenverhältnis 0,5; 0,45 MPa und 5 Minuten. Zehn Proben je Pressdauer, SD
5 Standardabweichung
6
7
8
9

10
11 Tabelle 6
12 Einfluss von Tannin (Mimosa und Quebracho) und Hexamin auf die Scherfestigkeit bei
13 170°C und 4 Minuten. SD: Standardabweichung
14
15

16 Tabelle 7
17 Viskosität der drei unter optimalen Bedingungen hergestellten natürlichen Holzklebstoffe bei
18 25 °C
19
20

21 Tabelle 8
22 Mechanische Eigenschaften von Maisstärke-NaOH-MT-H Klebstoff und handelsüblichen
23 Klebstoffen
24
25

26 Tabelle 9
27 Scherfestigkeit nach siebentägiger Lagerung in einem Vötsch Klimaraum (25°C, 65%, 80%
28 und 90% rel. Luftfeuchte). Zehn Proben je Harz. SD Standardabweichung
29
30

31 Tabelle 10
32 Scherfestigkeit vor und nach 2-stündiger Wasserlagerung. Zehn Proben je Harz. SD
33 Standardabweichung
34
35

36 Abb. 1
37 Schematische Darstellung der Herstellung der Prüfkörper mit quervernetzten Maisstärke-
38 Tannin-Klebstoffen. Schritt A: Pressdruck 0,45 MPa bei 180°C, Schritt B:
39 Scherfestigkeitsversuch nach 24-stündiger Lagerung im Vötsch Klimaraum (25°C und 65 %
40 Luftfeuchte)
41
42

43 Abb. 2
44 Festkörper-CP-MAS ¹³C NMR Referenzspektrum von Maisstärke und NaOH/Maisstärke
45
46

47 Abb. 3
48 TGA und DTG Kurven der Maisstärke-NaOH-Klebstoffe, $\beta=5^{\circ}\text{C}/\text{min}$
49
50

51 Abb. 4
52 Zeitlicher Verlauf des Speichermoduls (G') und Verlustmoduls (G'') des Maisstärke-NaOH-
53 Klebstoffs bei 25°C; 1rad/s und 1%.
54
55

56 Abb. 5
57 Schematische Darstellung der Reaktion zwischen Tannin und Hexamin.
58
59

60 Abb. 6
Festkörper-CP-MAS ¹³C NMR Referenzspektrum von Maisstärke und NaOH/Maisstärke,
Mimosatannin/Hexamin und Maisstärke/NaOH/MT/H
61
62

63 Abb. 7
64
65

1
2
3 Einfluss der Lagerungsdauer von Maisstärke-NaOH-MT-H Klebstoffen auf die
4 Scherfestigkeit
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

For Peer Review